



## MagShield® S Magnesium Hydroxide Powder in Polypropylene

To achieve a UL94 V(0) rating at 1/8" (3.2 mm) in polypropylene, a loading of 60% MagShield® S NB 10 Magnesium Hydroxide by weight of the total compound is usually required. MagShield S NB 10 is coated with stearic acid using a proprietary process to improve dispersion and to reduce mixing requirements.

### Processing Guidelines

Compounding trials in polypropylene (PP) homopolymer with a melt flow index of 22 at 230°C were conducted using a 40 mm Leistritz twin screw extruder. To obtain the whitest extrudate strands with the least porosity, the following guidelines are recommended:

- Processing temperature between 200°C and 225°C.
- Operating the extruder at low shear rate. The Leistritz extruder, which has a maximum rpm of 400, was operated at 150 rpm.
- Proper venting, preferably vacuum venting of at least 900 millibars near the die, is needed.

### Formulation and Results

Formulation	UL94 Data at 1/8" (3.2 mm)	
37.5% Polypropylene (22 MFI)	UL94 Rating at 1/8" (3.2 mm)	V(0)
60% MagShield® S NB 10	Total Afterflame Time (5 samples)	20 seconds
1.5% Calcium Stearate	Total Afterflame + Afterglow (5 samples)	20 seconds No Afterglow
1.0% PolyAd Preblend MM1252-25	Afterflame on any sample to holding clamp	No
	Ignited Cotton	No

### Stabilization and Processing Aids

Addition of stabilizers such as PolyAd Preblend MM1252-25 from Ciba Specialty Chemicals Corporation is helpful in providing good color in the extrudate. Other multi-component stabilizer packages may be used. Titanium dioxide (TiO<sub>2</sub>) may be added for additional whiteness/brightness.

Additional stearate processing aid can be added up to 1.0% to reduce extruder torque. In these trials, 1.0% calcium stearate was used.

See MagShield® technical data sheets for complete descriptions of our products. If you would like to speak with a technical representative, please call **800-648-7400** (inside the U.S.) or +1-410-780-5500.

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

**Martin Marietta Magnesia Specialties, LLC**

2700 Wycliff Road, Suite 320  
Raleigh, North Carolina 27607 USA  
Phone: (800) 648-7400  
[www.magnesiaspecialties.com](http://www.magnesiaspecialties.com)



MagShield® is a trademark of  
Martin Marietta Magnesia Specialties, LLC

Produced under a Quality Management System certified  
to ISO 9001:2015 by PRI Certification Registrar