



Product Specification

ELASTOMAG 170 MAGNESIUM OXIDE 296/1.76# Poly Bags

Rev 02/25/08

Property	Unit	Lower Specification	Upper Specification	Test Method
MAI		160	210	5-08
LOSS ON IGNITION	%	less than	8.5	5-15
CaO	%	less than	1.5	5-21
CHLORIDE	%	less than	0.5	5-25
-325 SCRIN	%	99.5	or greater	5-16
ASSAY	%MGO	96.0	or greater	5-13/5-14

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

Martin Marietta Magnesia Specialties LLC

8140 Corporate Drive, Suite 220
Nottingham, MD 21236
Phone: 800-648-7400 or 410-780-5500
FAX: 410-780-5777
www.magnesiaspecialties.com
e-mail: MagChem@martinmarietta.com
02/08 hrc

Martin Marietta Magnesia Specialties

Elastomag is a trademark of
Martin Marietta Magnesia Specialties, LLC

Copyright © 2008 by Martin Marietta Magnesia Specialties, LLC