



# MagChem® 50 SC Specialty Magnesium Oxide

<b>DESCRIPTION</b>	MagChem 50 SC is a medium reactive magnesium oxide powder formulated for applications requiring maximum consistency in chemical, physical properties, and reactivity.	
<b>USES</b>	MagChem 50 SC is used in manufacturing grain oriented steel for high performance electrical transformers, specialty ceramics and coatings.	
<b>COMPOSITION</b>		<b><u>Specifications</u></b>
	Magnesium Oxide (MgO), %	98.0 min.
	Calcium Oxide (CaO), %	0.60 max.
	Silicon Oxide (SiO <sub>2</sub> ), %	0.50 max.
	Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	0.30 max.
	Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	0.20 max.
	Chloride (Cl), %	130 (± 30)
	Sulfate (SO <sub>4</sub> ), %	0.15 max.
	Sodium (Na), ppm	200 max.
	Potassium (K), ppm	200 max.
	Fluoride (F), ppm	150 max.
	Boron (B), ppm	750 (± 150)
	Carbon (C), %	0.20 max.
	Loss on Ignition, %	2.0 max.
<b>PHYSICAL PROPERTIES</b>		<b><u>Specification</u></b>
	Loose Bulk Density, lb/ft <sup>3</sup> (g/cm <sup>3</sup> )	12 – 30 (0.19 – 0.48)
	Median Particle Size, microns	1.0 max.
	BAT, seconds	45 - 55
	CAA, seconds	(Typical) 54
	Screen Analysis:	
	% Passing 200 Mesh	99.75 min.
	% Passing 325 Mesh	99.5 min.
<b>PACKAGING</b>	Martin Marietta Magnesia Specialties packages this product in 50 pound bags. Please contact a sales representative for information on detailed packaging offerings and specifications.	
<b>STORAGE</b>	Store in dry place. Exposure to moisture may cause caking.	

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

### Martin Marietta Magnesia Specialties, LLC

8140 Corporate Drive, Suite 220  
Baltimore, Maryland 21236 USA  
Phone: (800) 648-7400 or (410) 780-5500  
Fax: (410) 780-5777  
Email: [MagChem@martinmarietta.com](mailto:MagChem@martinmarietta.com)  
[www.magnesiaspecialties.com](http://www.magnesiaspecialties.com)

